

## PRODUCT DATA SHEET

### MULE-HIDE .045" and .060" STANDARD BLACK EPDM MEMBRANE

#### PRODUCT DESCRIPTION

Mule-Hide Standard Black EPDM membranes are high performance non-reinforced membranes that stand up to tearing, impacts, punctures and normal roof traffic. The elastomeric properties of the EPDM membranes compensate for thermal shock and building movement. EPDM membranes provide excellent resistance to ozone and aging. The EPDM membranes are manufactured in accordance with the guidelines established by the RMA (Rubber Manufacturers Association) and meet or exceed the ASTM Standard Specification D 4637. **Mule-Hide Standard Black EPDM membranes are Fire Retardant (FR) membranes specially formulated to inhibit spread of flame and meet or exceed code body testing criteria for fire retardant roofing membranes.**

#### BASIC USES

Can be installed as a new elastomeric roofing membrane in Ballasted, and Fully Adhered roofing systems.

#### SPECIFICATIONS

Mule-Hide .045" and .060" thick Standard Black EPDM Membranes.

Physical Properties	Test Method	Standards	Typical Values	
			.045	.060
Tolerance on Nominal Thickness, %	ASTM D 412	± 10	+ 10	+ 10
Weight, lbm/ft <sup>2</sup> (kg/m <sup>2</sup> )			0.26 (1.3)	0.35 (1.7)
Tensile Strength, min, psi(Mpa)	ASTM D 412	1305 (9)	1550 (10.7)	1550 (10.7)
Elongation, Ultimate, min, %	ASTM D 412	300	480	480
Tear Strength, min, lbf/in (kN/m)	ASTM D 624 (Die C)	150 (26.3)	200 (35.0)	200 (35.0)
Factory Seam Strength, min.	ASTM D 816 (Modified)	Membrane Rupture	Membrane Rupture	Membrane Rupture
Resistance to Heat Aging* Properties after 4 weeks @ 240°F(116°C)	ASTM D 573			
Tensile Strength, min, psi(MPa)	ASTM D 412	1205(8.3)	1500(10.3)	1500(10.3)
Elongation, Ultimate, min, %	ASTM D 412	200	225	225
Tear Resistance, min, lbf/in(kN/m)	ASTM D 624	125(21.9)	215 (37.6)	215 (37.6)
Linear Dimensional Change, max, %	ASTM D 1204	± 1.0	-0.4	-0.4
Ozone Resistance* Conditions after exposure 100 pphm Ozone in air for 168 hrs @ 104°F(40°C) Specimen is at 50% strain	ASTM D 1149	No Cracks	No Cracks	No Cracks
Brittleness Temp., max, deg. F (deg.C)	ASTM D 746	-49 (-45)	-67 (-55)	-67 (-55)
Resistance to Water Absorption* After 7 days immersion @ 158°F (70°C), Change in mass, max, %	ASTM D 471	+8, -2	+2.0	+2.0
Water Vapor Permeability* MAX. perm mils	ASTM E 96 (Proc. B or BW)	0.10	0.05	0.05
Resistance to Outdoor (Ultraviolet) Weathering Xenon-Arc, 4000 hrs. exposure, 176°F (80°C) black panel temperature	ASTM G 155	No Cracks No Cracking	No Cracks No Cracking	No Cracks No Cracking
*Not a Quality Control Test due to the time required for the test or the complexity of the test. However, all tests run on a statistical basis to ensure overall long-term performance of the sheeting.				

Form # PDS-E-1A  
Date 01/01/2008

### MULE-HIDE PRODUCTS CO., INC.

P.O. Box 1057, Beloit, WI 53512-1057 • 608/365-3111 • Fax: 608/365-7852

**MULE-HIDE .045" and .060" STANDARD BLACK EPDM MEMBRANE**

**SYSTEM BENEFITS**

- 1) Economical system
- 2) Ease of Installation
- 3) Outstanding Weatherability
- 4) Lightweight
- 5) Can eliminate tear-off of existing roof if appropriate.

**SIZES**

Roll sizes for .045" and .060" Standard Black EPDM membranes are widths of 7', 10', 20', 30', 40' and 50' and lengths of 50', 100' and 150'.

**SYSTEM ACCESSORIES**

A full line of accessories is available from Mule-Hide including flashings, membranes, bonding adhesives, splice adhesives, In-Seam tapes, cured cover tapes, uncured flashing tapes, tape primer, lap sealant, seam cleaner, water cut-off mastic, pourable sealer, pre-formed pipe boots, walk pads, termination bar, fasteners and plates.

**CODE APPROVALS**

The Standard Black EPDM membrane may be provided with UL and FM labels. Both UL and FM classified assemblies are available (ex: FM 1-60 and 1-90, UL Class A, B and C).

**INSTALLATION INSTRUCTIONS**

Install the EPDM membrane in accordance with the appropriate current printed Mule-Hide specification. Carefully review and follow the installation instructions in the Mule-Hide Specifications Manual. All flashing details are to be installed in accordance with Mule-Hide's current published details.

**TECHNICAL SERVICES**

Contact Mule-Hide Products Co., Inc. at 608/365-3111 for additional information.

**DISCLAIMER**

The statements provided concerning the material shown are intended as a guide for material usage and are believed to be true and accurate. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. Since the manner of use is beyond our control, Mule-Hide does not make nor does it authorize anyone to make any warranty of merchantability or fitness for any particular purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material except that it conforms to Mule-Hide's physical properties. Buyer and user accept the product under these conditions and assume the risk of any failure, any injury of person or property (including that of the user), loss or liability resulting from the handling, storage or use of the product whether or not it is handled, stored or used in accordance with the directions or specifications. Mule-Hide must be notified in writing of any claims and be given the opportunity to inspect the complaint or failure before repairs are made.

Form # PDS-E-1A  
Date 01/01/2008